

# AFCONA - 2763



## Chemical Composition

Silicone defoamer with modification of Fluorocarbon.

## Product general description

A moderate defoamer with less side effects.

## Product properties

AFCONA-2763 prevents the formation of foam and blisters during manufacturing and application. It has the combination of good defoaming as well as compatibility with most resin system. It is recommended for medium viscosity applications applied by spray and brush.

AFCONA - 2763 is recommended for brush and conventional spray application, very suitable also for systems ranging from low polar to high polar. It also gives reasonable good compatibility and clarity to the systems.

- 1) Epoxy, solvent based or solventless
- 2) polyurethane systems for wood, plastic, flooring and car refinish
- 3) airless spray coatings
- 4) stoving paints for general industrials
- 5) UV curing system especially for acrylate epoxy
- 6) High viscosity systems.

## Product Specification

Solvent	DIBK/MIBK/S.B.P. Spirit
Density	0.77 – 0.81 g /cm <sup>3</sup> (20°C)
Flash point	35°C
Appearance	Clear to slightly yellow liquid (25°C)

## Addition and dosage

0.1 - 0.7% on total formulation. In general under normal conditions, the dosage is 0.2 – 0.5% based on total formulation.

## Incorporation

To prevent foaming AFCONA-2763 can be added prior to processing. If it is added to the finished product, care must be taken to ensure uniform distribution.

## Storage

AFCONA-2763 should be stored in a cool and dry place. When kept in an original unopened container, it will keep up for 5 years from the date of manufacture. The expiry date is indicated on the container.

## Packaing

20kg and 160kg non-returnable containers

## AFCONA ADDITIVES

Web Site : [www.afcona.com](http://www.afcona.com)

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.