

# AFCONA - 3755



## Chemical Composition

Polyacrylic polymer.

## Product general description

Wetting, leveling and flow control agent for solvent-based coatings with very effective defoaming property.

## Product Properties:

AFCONA – 3755 is a special polyacrylic levelling agent. It was designed for application where levelling and defoaming are both important such as coil and can coatings. It also can be use in other foam sensitive systems.

AFCONA-3755 has below properties:

- 1) Very good initial levelling and improve leveling property before touch dry.
- 2) Very good in defoaming and anti-foam properties.
- 3) No influent in overcoating adhesion property.

Unlike normal levelling agents where it will also acts as good foam stabilizing, AFCONA – 3755 is a very effective defoamer as well as unique levelling property.

AFCONA-3755 is suitable for below systems:

- 1) Coil and can coating
- 2) For further improve substrate wetting and anti-crater properties, combination with AFCONA -3670 or AFCONA -3700 are recommended.
- 3) All baking systems
- 4) Matted topcoat and primer of wood coating
- 5) Not suitable for unpigmented high gloss system as due to it high efficiency of defoaming, it also cause in-can haziness.

## Product Specification

Non-volatile matter	50 - 54%(150°C,0.5h)
Solvent	DIBK/Xylene
Density	0.95 – 0.99 g/cm <sup>3</sup> (20°C)
Flash point	39°C
Gardner color	Max.6
Appearance	Transparent to slight yellowish liquid(25°C)

## Addition and dosage

0.50 – 2.00% on total formulation. In general, under normal conditions, the dosage is 0.50 – 0.80% based on total formulation.

## Incorporation

AFCONA-3755 should be added at the end of the batch preparation.

## Storage

AFCONA-3755 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.

## Packaging

25kg and 190 kg non-returnable containers

AFCONA ADDITIVES

Web Site : [www.afcona.com](http://www.afcona.com)

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.