

AFCONA - 5065



Chemical Composition

High-molecular weight unsaturated carboxylic acid, combined with a very compatible organically modified polysiloxane.

Product general description

Wetting and dispersing additive to prevent flooding and sedimentation of pigments.

Product Properties:

AFCONA-5065 is a very effective dispersants. The performance is close to high molecular weight dispersant. However, this is not always close enough. It is recommended for medium to high polar system, such as PU, UPE, UV, NC, Baking Paints and Acid Curing. This product also widely is used in printing ink. Not recommended for air-drying alkyds, because incompatibility with these systems.

AFCONA – 5065 has below special properties and recommended in below systems::

- 1) AFCONA-5065 can act as additive for post addition to correct flooding and floating of coatings. It will re-flocculate those inorganic pigments to the same degree as the organic pigments in order they can move in the same speed. Using this method, to solve flooding and floating, sometime can affect gloss of the dry film, especially when the dosage is higher than 0.8% on total formulation.
- 2) AFCONA-5065 also widely used together with high molecular weight dispersants, such as AFCONA-4010, AFCONA-4050 or AFCONA-4046, as an effective co-grinding dispersant in a ratio of 1:1 to 3:1(High Mol Weight Dispersant : AFCONA-5065). However, for foam sensitive systems like coil coatings and floor coatings AFCONA – 5066 is a better recommendation.
- 3) AFCONA-5065 is not compatible with white spirit or paints which are diluted with white spirit.

Product Specification

Non-volatile matter	50 - 54% (150°C,0.5h)
Solvent	Alkylbenzene/ Diisobutylketone
Density	0,94 – 0,96 g/cm ³ (20°C)
Acid Value	80 - 150 mg KOH/g
Flash point	41°C
Appearance	Clear to slightly hazy, brownish liquid (25°C)

Addition and dosage

0.5 - 2.5% based on inorganic pigments or
0.1 - 1.0% based on total formulation,
normally at 0.5% based on total formulation.

Incorporation

AFCONA-5065 should be added prior to the dispersion process. High shear force mixing is recommended when added after process.

Storage

AFCONA-5065 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.

Packaging

25kg and 190 kg non-returnable containers

AFCONA ADDITIVES

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.