

AFCONA - 2035



Chemical Composition

Silicone containing defoaming polymer modified with fluorocarbon.

Product general description

A moderate defoamer with minimum side effects.

Product Properties:

AFCONA-2035 prevents the formation of foam and blisters during manufacturing and application. It has the combination of good defoaming as well as compatibility with most resin system. It is recommended for medium viscosity applications applied by spray and brush.

AFCONA-2025, AFCONA-2035 and AFCONA 2040 have almost the same chemical structure with different modification. However, the performance is very different in some systems. We recommend trying all three of them in order to be sure to choose the most suitable defoamer for your system. However, above all, in most cases, AFCONA-2035 or AFCONA 2040 performs better.

AFCONA-2035 is recommended for brush and conventional spray application, very suitable also for systems ranging from low polar to high polar.

Recommended applications:

- 1) air drying systems, physical drying systems, based on acrylic, vinyl or chlorinated polymers
- 2) polyurethane systems for wood, plastic and car refinish
- 3) NC lacquers and acid curing for wood coatings and general industrial
- 4) airless spray coatings

Product Specification

Solvent	Diisobutyl ketone
Density	0.80 – 0.82 g/cm ³ (20°C)
The refractive index	1.410 – 1.420 (25°C)
Flash point	49°C
Appearance	Clear, Colourless liquid(25°C)

Addition and dosage

0.1 – 1.0% on total formulation. In general, under normal conditions, the dosage is 0.2 – 0.4% based on total formulation.

Incorporation

AFCONA-2035 should be added prior to processing. If added subsequently, good dispersion must be ensured

Storage

AFCONA-2035 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.

Packaging

20kg and 160 kg non-returnable containers

AFCONA ADDITIVES

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.