

AFCONA - 4047



Chemical Composition

Modified polyurethane polymer

Product general description

High molecular weight polymeric dispersant for deflocculation of all type of pigments

Product Properties

AFCONA-4047 is a highly effective polymeric dispersant for stabilizing inorganic and organic pigments as well as carbon blacks. It has very good stability performance, through effective steric hindrance, on all types of pigments.

This results in:

- improved gloss and DOI
- reduced flooding problems
- higher colour strength
- lower viscosity

AFCONA – 4047 has below special properties and recommended in below systems:

- 1) AFCONA – 4047 is compatible with almost all solvent-based resins with the exception of some thermoplastic acrylics.
- 2) Due to the excellent pigment stabilizing performance, AFCONA – 4047 is extremely suitable for high quality coatings, such as OEM and refinish, can coating, coil coatings and other high quality coatings. However, it also can be used in epoxy, UPE, Polyurethane and other resin systems.
- 3) AFCONA – 4047 gives lower milling viscosity comparing to AFCONA-4046.
- 4) AFCONA – 4047 can be used as effective dispersant for universal pigment concentrates preparation. For these we recommended a combination with AFCONA-1102.

Note: AFCONA – 4047 may be slightly hazy or crystallized at temperatures below 5° C. Heat up and well-mixed, This will not influence the performance.

Product Specification

Non-volatile matter 34 - 36%(150°C, 0.5h)

Solvents	Butylacetate / Methoxy Propyl Acetate/Sec-butanol
Amine Value	10 – 20 mgKOH/g
Flash point	38°C
Gardner colour	Max.4
Appearance	Clear to slightl hazy, yellow liquid(25°C)

Addition and dosage

Calculation method for the required amount of active ingredient on pigment.

TiO2	:2 - 3%
Other inorganic pigments	:2 - 4%
Organic pigments	:20 - 40%
Carbon blacks	:20 - 60%

Incorporation

AFCONA-4047 should be incorporated in the mill base before adding the pigments.

Storage

AFCONA-4047 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.

Packaging

25kg and 190 kg non-returnable containers

For product safety information: please take reference of SDS.

AFCONA ADDITIVES

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.