

AFCONA-4560



Chemical Composition

Modified polyacrylate polymer.

Product general description

High molecular weight dispersant for decorative and industrial paints that prevents pigment flocculation and is unaffected by pH value.

Product Properties

AFCONA-4560 is a high molecular weight dispersant. It provides excellent stability for inorganic and organic pigments, as well as carbon blacks. Its effective steric hindrance effect provides outstanding stabilizing performance for all types of pigments.

AFCONA-4560 offers the following advantages:

- 1) Higher gloss
- 2) Higher colour strength
- 3) Anti-flocculation
- 4) Prevention of floating and flooding

AFCONA-4560 is pH independent and broadly compatible with most water-based decorative coating systems. It does not affect the water resistance of the coating. It is completely water-soluble and does not require neutralization. However, neutralization can enhance its viscosity-reducing properties.

When AFCONA-4560 is stored at or above 60°C, its solubility in water decreases. Therefore, the grinding temperature should be kept below 60°C to ensure its high efficiency. Of course, once the temperature drops, its solubility in water will recover.

AFCONA-4560 is recommended for the preparation of resin-free pigment pastes and for use in various waterborne industrial paints. It can be combined with AFCONA-6225 for better cost savings without compromising dispersion quality. Please refer to the application section for guide formulations.

Note: AFCONA-4560 may become slightly hazy when stored at or below 5°C, but that does not affect its quality.

Product Specification

Non-volatile matter	38 - 42% (150°C, 0.5h)
Solvent	Water
Density	1.02 - 1.06 g/cm ³ (20°C)
Amine value	20 - 28 mg KOH/g
Gardner color	Max.6
Flash point	>100°C
Appearance	Clear, yellowish/slightly hazy liquid (25°C)

Addition and dosage

Calculation method for the required amount of active ingredient on pigment:

TiO ₂	: 2-3%
Other inorganic pigments	: 2-4%
Organic pigments	: 20-40%
Carbon blacks	: 20-60%

Incorporation

AFCONA-4560 should be incorporated in the mill base before adding the pigments.

Storage

AFCONA-4560 shall be stored in cool, dry and freeze-proof place. Shelf-life is 3 years from the date of manufacturer, if kept in original and unopened container. The expiring date is indicated on the package.

Packaging

25kg and 200kg non-returnable containers

For product safety information: please refer to the product SDS.

AFCONA ADDITIVES

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.