

AFCONA-4701



Chemical Composition

Modified polyacrylate polymer based on CRP technology.

Product general description

High molecular weight polymeric dispersant for de-flocculation of all types of pigments.

Product Properties

AFCONA-4701 is an effective polymeric dispersant based on AFCONA CRP technology. It has excellent performance in stabilizing inorganic and organic pigments. It has very good stability in carbon black dispersion, achieving very high jetness. In metallic systems, it provides a golden undertone in high-grade channel black dispersion.

AFCONA-4701 offers the following advantages:

- Improved gloss and DOI, reduced haziness
- Prevention of flooding problems
- Higher colour strength
- Lower viscosity

AFCONA-4701 is an improved version of AFCONA-4700 for organic pigments. In carbon black, both products have almost the same performance.

AFCONA-4701 is recommended for:

- 1) AFCONA-4701 can be used in nearly all known solvent-based resin systems.
- 2) AFCONA-4701 is often recommended for automotive OEM and refinish paints, as well as various high-grade industrial coatings.
- 3) The excellent compatibility of AFCONA-4701 also enables it to be used in preparing universal color concentrates. For example, its color concentrates are highly compatible with difficult-to-match systems containing thermoplastic acrylic or NC.
- 4) Due to its special anchoring end groups, AFCONA-4701 itself has a relatively dark appearance, which does not affect the color of the final coating during actual dispersion.

Note: AFCONA-4701 may become slightly hazy when stored at or below 5°C. That will not influence the dispersing quality.

Product Specification

Non-volatile matter	48 - 52% (150°C, 0.5h)
Solvent	Propylene glycol methyl ether acetate
Density	1.01 - 1.05 g/cm ³ (20°C)
Amine Value	15 - 25 mg KOH/g
Flash point	44°C
Appearance	Transparent, brownish liquid (25°C)

Addition and dosage

Calculation method for the required amount of active ingredient on pigment:

TiO ₂	: 2-3%
Other inorganic pigments	: 2-4%
Organic pigments	: 20-40%
Carbon blacks	: 20-60%

Incorporation

AFCONA-4701 should be incorporated in the mill base before adding the pigments.

Storage

AFCONA-4701 shall be stored in cool and dry place away from direct sunlight. Shelf-life is 5 years from the date of manufacturer, if kept in original and unopened container. The expiring date is indicated on the package.

Packaging

30kg and 200kg non-returnable containers

For product safety information: please take reference of SDS.

AFCONA ADDITIVES

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.